

# SS-1 Product Data Sheet



## Description and Physical Properties

SS-1 is an anionic slow setting asphalt emulsion designed for use as a tack coat, in fine-graded mixes, dust control, fog seal and specialty applications. Physical Properties:

- C.A.S. Number: 8052-42-4
- Boiling Point (F): 212°F
- Specific Gravity (H<sub>2</sub>O=1): 1.01
- Percent Volatile: 0
- Solubility In Water: Soluble
- Appearance and Odor: Brown Liquid, Faint Petroleum Odor
- Flammability: Non-flammable in water-based state

## Recommended Use

SS-1 emulsions are used for a variety of purposes. Slow setting emulsions are the most stable of emulsions, and generally can be diluted with water and mixed with mineral fillers and aggregates. For all paving uses, the air and pavement temperatures at construction should be sufficiently high to allow the emulsion to fully cure. TxDOT states that no asphalt binders should be applied during rain or imminent threat of rain.

Specifications Conforms to Texas Department of Transportation Specifications-Item 300.2:

Property	Test Procedure	Min	Max
Viscosity, Saybolt Furol, 77°F, sec	T72	20	100
Sieve test, %	T59	-	0.1
Miscibility	T59	Pass	
Cement mixing, %	T59	-	2.0
Freezing test, 3 cycles <sup>1</sup>	T59	Pass	
Distillation test:	T59		
Residue by distillation, % by wt.		60	-
Oil distillate, % by volume of emulsion		-	0.5
Tests on residue from distillation:			
Penetration, 77°F, 100 g, 5 sec.	T49	120	160
Solubility in trichloroethylene, %	T44	97.5	-
Ductility, 77°F, 5 cm/min., cm	T51	100	-

<sup>1</sup> Applies only when the Engineer designates material for winter use.

## Storage and Handling

The water-based emulsion should not be exposed to overheating. The anionic emulsion is a chemically stabilized system, so care should be taken not to upset the chemical balance with contamination by chemicals, over-exposure to air, or adverse mechanical or thermal conditions. Before being filled, tanks and trucks should be examined for possible contaminants. Recommended use and storage temperatures are given in the table.

Recommended Temperatures	Min	Max
Storage	50°F	140°F
Application	50°F	130°F

## Martin Asphalt Quality

Through Martin Asphalt, you get **Everything Asphalt**—a full range of products. In addition, you receive technical assistance in selecting the right materials and application. The company's AASHTO Certified Laboratory makes sure the products meet your specifications. And your products are delivered both on spec and on time via Martin's Gulf Coast network of production plants, storage facilities and transportation fleet including ocean-going and inland barges, rail cars and tanker trucks. For more information, contact us.